

Test Report Date: JUN.05,2013 No.: SHHG1305019617SD Page: 1 of 7

KENMISSYR LLC

125F TRADE COURT #48 MOORESVILLE, NC 28117

The following sample(s) was/were submitted and identified by the client as:

Sample Description : EVA INTERLOCKING FOAM TILES UPPERCASE

LETTERS NUMBERS 0-9

Color : BLUE, RED, GREEN, YELLOW, ORANGE, PURPLE

Style/ Item No. : 12UAN1-10M

: NOT FOR CHILDREN UNDER 3 YEARS Labeled Age Grading

Requested Age Grading : 3+

Age Group Applied in Testing :2+YEARS

Country of Destination : USA

Sample Receiving Date : MAY.30,2013

Testing Period : MAY.30,2013 TO JUN.05,2013

Test Performed : SELECTED TEST(S) AS REQUESTED BY APPLICANT Test Requested : SELECTED TEST(S) AS REQUESTED BY APPLICANT : FOR FURTHER DETAILS, PLEASE REFER TO THE Test Result(s)

FOLLOWING PAGE(S)

Conclusion : THE SUBMITTED SAMPLE MET THE TEST

REQUIREMENT.

Signed for and on behalf of SGS-CSTC Ltd.

Philemon ZHU Technical Manager

3rd Building,No.889,Yishan Road, Xuhui District Shanghai,China 200233 t (86-21)61402666*2013 f (86-21)54500353 中国 · 上海 · 徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353



Test Report No.: SHHG1305019617SD Page: 2 of 7 Date: JUN.05,2013

Test Conducted:

ASTM F963 - 11

AS SPECIFIED IN ASTM F963-11 STANDARD CONSUMER SAFETY SPECIFICATION ON TOYS SAFETY

Clause Relevant to Sample.

<u>Clause</u>	<u>Description</u>	Result
4	Safety Requirements	
4.1	Material Quality (Visual Examination)	<u>Pass</u>
4.2	Flammability Test	Pass (See Note 1)
4.3	Toxicology	Pass (See Note 2)
4.6	Small Objects	
4.6.1	Small Objects	<u>Pass</u>
4.7	Accessible Edges	<u>Pass</u>
4.9	Accessible Points	<u>Pass</u>
5	Safety Labeling Requirements	
5.2	Age Grading Labeling	<u>Pass</u>
5.16	Promotional Materials	<u>Pass</u>
7	<u>Producer's Markings</u>	
7.1	Producer's Markings	<u>Pass</u>
8	<u>Test Methods</u>	
8.5	Normal Use Testing	<u>Pass</u>
8.7	Impact Test	<u>Pass</u>
8.8	Torque Test	<u>Pass</u>
8.9	Tension Test	<u>Pass</u>

Note 1:

Flammability Test (Clause 4.2)

Flammability Test on Solid

Burning Rate (inch/sec) <u>Sample</u> Foam mat

*BURNING RATE HAS BEEN ROUNDED TO THE NEAREST ONE TENTH OF AN INCH PER SECOND.

Requirement: A toy / component is considered a "flammable solid" if it ignites and burns with a selfsustaining flame at a rate greater than 0.10 in/sec along its major axis.

N.B.: - Only applicable clauses were shown.

ent is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.
electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of many features and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of the state of the company's findings at the time of the state of the company is the state of the state of the state of the company's sole responsibility is to its Client and this document does not exonerate parties to a transaction sing all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Orized alteration? Orgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. The company or the company of the compan

Lid. 3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 t (86-21)61402666*2013 f (86-21)54500353 中国・上海・徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353



Test Report No.: SHHG1305019617SD Page: 3 of 7 Date: JUN.05,2013

Note 2:

American Society for Testing and Materials -ASTM F 963-11 - total Lead in Substrate Materials

Test Method: With reference to CPSC Test Method: CPSC-CH-E1002-08.1. Analysis was performed by ICP-OES.

Test Item(s) Total Lead (Pb)	<u>Limit</u> 100	<u>Unit</u> mg/kg	MDL 20	<u>001</u> ND	<u>002</u> ND	<u>003</u> ND
Test Item(s)	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>004</u>	<u>005</u>	<u>006</u>
Total Lead (Pb)	100	ma/ka	20	ND	ND	ND

American Society for Testing and Materials –ASTM F 963-11 – soluble heavy metal in Substrate Materials/paint and similar surface-coating materials

Test Method: Soluble Heavy Metal contents (Clause 4.3.5) - Sample was extracted by dilute hydrochloric acid in accordance with ASTM F 963-11(Clause 8.3), analysis was performed by ICP-OES.

Test Item(s)	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>001</u>	<u>002</u>	<u>003</u>
Soluble Lead (Pb)	90	mg/kg	5	ND	ND	ND
Soluble Antimony (Sb)	60	mg/kg	5	ND	ND	ND
Soluble Arsenic (As)	25	mg/kg	2.5	ND	ND	ND
Soluble Barium (Ba)	1000	mg/kg	10	ND	ND	ND
Soluble Cadmium (Cd)	75	mg/kg	5	ND	ND	ND
Soluble Chromium (Cr)	60	mg/kg	5	ND	ND	ND
Soluble Mercury (Hg)	60	mg/kg	5	ND	ND	ND
Soluble Selenium (Se)	500	mg/kg	10	ND	ND	ND
Test Item(s)	<u>Limit</u>	<u>Unit</u>	<u>MDL</u>	<u>004</u>	<u>005</u>	<u>006</u>
Soluble Lead (Pb)	90	mg/kg	5	ND	ND	ND
Soluble Antimony (Sb)	60	mg/kg	5	ND	ND	ND
Soluble Arsenic (As)	25	mg/kg	2.5	ND	ND	ND
Soluble Barium (Ba)	1000	mg/kg	10	ND	ND	ND
Soluble Cadmium (Cd)	75	mg/kg	5	ND	ND	ND
Soluble Chromium (Cr)	60	mg/kg	5	ND	ND	ND
Soluble Mercury (Hg)	60	mg/kg	5	ND	ND	ND
Soluble Selenium (Se)	500	mg/kg	10	ND	ND	ND

In the issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions. electronic format documents, subject to Terms and Conditions for Electronic Documents at twww.sgs.com/terms e-document.htm. Attention is drawn to the limitation of motionaries and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of graph which the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction ing all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. or produced in the containing all their rights and obligations under the transaction of the content of the content of the document is unlawful and offenders may be prosecuted to the fullest extent of the law. was stated the read this shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days only.

Lid. 3rd Building, No. 889, Yishan Road, Xuhui District Shanghai, China 200233 t (86-21)61402666*2013 f (86-21)54500353 中国・上海・徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353



Test Report No.: SHHG1305019617SD Page: 4 of 7 Date: JUN.05,2013

Notes:

(1) Results shown are of the adjusted analytical results

Test Part Description:

Specimen No.	SGS Sample ID	Description
1	SHA13-101694.001	Green foam mat
2	SHA13-101694.002	Yellow foam mat
3	SHA13-101694.003	Purple foam mat
4	SHA13-101694.004	Blue foam mat
5	SHA13-101694.005	Orange foam mat
6	SHA13-101694.006	Red foam mat

Remarks:

- (1) 1 mg/kg = 0.0001%
- (2) MDL = Method Detection Limit
- (3) ND = Not Detected (< MDL)
- (4) "-" = Not Regulated

3rd Building,No.889,Yishan Road, Xuhui District Shanghai,China 200233 t (86-21)61402666*2013 f (86-21)54500353 中国・上海・徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353



Test Report

No.: SHHG1305019617SD

Date: JUN.05,2013

Page: 5 of 7

Sample Photo:





3rd Building,No.889,Yishan Road, Xuhui District Shanghai,China 200233 t (86-21)61402666*2013 f (86-21)54500353 中国・上海・徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353



Test Report No.: SHHG1305019617SD Date: JUN.05,2013 Page: 6 of 7






3rd Building,No.889,Yishan Road, Xuhui District Shanghai,China 200233 t (86-21)61402666*2013 f (86-21)54500353

中国・上海・徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353



Test Report No.: SHHG1305019617SD Page: 7 of 7 Date: JUN.05,2013





End of Report

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions. htm and, for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms-e-document.htm. Attention is drawn to the limitation of its intervention of the interventi

3rd Building,No.889,Yishan Road, Xuhui District Shanghai,China 200233 t (86-21)61402666*2013 f (86-21)54500353 中国・上海・徐汇区宜山路889号3号楼 邮编:200233 t (86-21)61402666*2013 f (86-21)54500353